

**PROCEDURES OF CELLULAR LABELLING WITH PARAMAGNETIC
COMPLEXES FOR MRI APPLICATIONS**

SUMMARY OF THE INVENTION

MRI visualisation of cellular systems requires internalisation of a large number of paramagnetic complex units. It has been found that the most efficient route for introducing large amounts of metal complexes into a cell is to internalise them in the form of finely divided particulate. Therefore, internalisation may be carried out, depending on the characteristics of the cell type, through: a) phagocytic activity or b) receptor-stimulated endocytosis. In the latter case, units responsible for targeting the cell surface will have to be bound to the particulate surface, which will optionally be coated by means of procedures similar to those used for the iron oxides commonly employed as MRI contrast agents. Once internalised, the particles will be gradually degraded by the activity of appropriate enzymes or anyhow by suitable effectors inside the surrounding micro-environment, thus releasing the single unities of the paramagnetic complex as schematically disclosed in Fig. 6. The presence of the particulate in the cell can easily be detected with the MRI technique by T2-weighted sequences, while the presence of free complex units, also called MR-Imaging Probes, is more easily revealed by T1-weighted sequences. The enzyme gradually degrading the particles may naturally occur in the concerned cell or it may be specifically expressed by known molecular biology procedures or it may be administered in a form which localises in the concerned cellular compartments.

BACKGROUND OF THE INVENTION

Paramagnetic complexes of transition metals (particularly Mn(II) and Mn(III)) and of lanthanides (particularly Gd(III)) are used as Contrast Agents (CA) in Magnetic Resonance Imaging due to their ability of inducing a

remarkable enhancement in the relaxation rate of tissue protons. In most cases they have extracellular distribution and have proved particularly valuable for evaluating organs and tissues perfusion, or for revealing any abnormalities in the hemato-encephalic barrier and so on. In angiographic applications, CA
5 segregation in the vasal compartment through non-covalent interaction with serum albumin is sought. In less cases, the diagnostic potential is related to the intracellular distribution of the CA, as is the case with hepato-specific agents which, upon active transport, enter the hepatocytes but not metastases which may be present in this organ. A further example is the internalisation of a
10 paramagnetic complex inside red blood cells by osmotic shock. This procedure provides red blood cells containing a large number of paramagnetic complexes, which may give important information on flow, volume, etc. in MRI imaging.

Recently, attention has been focused on the possibility of labelling
15 specific cell types in order to visualise them in MRI procedures. An example of application connected with an improvement in current diagnostic protocols relates to the targeting on the receptors that are over-expressed in tumour cells. In these cases, cellular labelling can be carried out either through accumulation of CA on the outer surface of the cell membrane, or through
20 internalisation by means of suitable regenerable receptors. Other applications of great interest concern the possibility of monitoring cellular homing, with interesting perspectives in tracking stem cells. Highly innovative is also the possibility of using cellular labelling to evidence occurred transfection in gene therapy. Targeting of therapeutic genes is an extremely interesting possibility
25 and related studies are expected to markedly develop in the future. Independently of the gene therapy technology which will prevail (virus or proteins/DNA complexes or liposomes/DNA adducts) it will be necessary to develop suitable gene transfer indicators. To date, "in vitro" studies rely on

procedures involving the use of genes that express enzymes, such as β -galactosidase or a green fluorescent protein, in the infected cells. In other words, in the infection procedure of a given cell, use is made of a construct containing not only the gene specific for the treatment of the diseases, but also

5 the gene for the indicator that will provide information on the occurred transfer of the administered gene material into the nucleus. Due to the high spacial resolution ability of MRI, this procedure has of course been considered to monitor gene transfer processes. Meade et coll. used a Gd-HPDO3A derivative containing one galactose unit cleaved by the enzyme β -

10 galactosidase. The transformation induces a change of the complex relaxivity which can be revealed by MR image. In practice, this approach is apparently limited by several factors, such as the limited relaxivity enhancement and, even more, by the difficulties in specifically introducing the complex in the concerned cells (in the paper by Meade et coll. the complex is directly injected

15 into the oocytes transfected with the β -galactosidase gene). Other Authors suggested the use of magnetite particles as gene transfer indicators by means of overexpressed transferrin receptors. The concerned protein acts as a carrier for the internalisation of the magnetic particle. One limit to this approach is that it is preferable to observe a positive contrast enhancement rather than a

20 negative one, as is the case with these particles acting on the change in magnetic susceptibility. Moreover, the cell-internalization of large amount of iron yields serious concern about its metabolic fate.

Therefore, there is a need for developing new cellular labelling strategies based on the release of paramagnetic complexes (positive contrast)

25 endowed with specific tropism towards the concerned cells and able to attain a high contrast in the resulting MRI images.

DESCRIPTION OF THE INVENTION

As mentioned in the introduction, a gene encoding for an indicator

enzyme is often used in cellular labelling procedures. On the other hand detection of a given enzyme overexpression is often of high diagnostic value in a number of pathologies. For MRI observations it is necessary that the presence of a given enzyme induces meaningful variations in water protons relaxation. To be more effective, this process should convert a
5 “relaxometrically silent” species into a “relaxometrically active” species.

It has now been found that this objective can be obtained by means of insoluble particles comprising paramagnetic complexes of Lanthanide or transition metal chelates, as MR-Imaging Probes, administered in form of
10 particulate which is internalised by cells where they are degraded enzymatically or by effectors in the environment surrounding them, giving rise to water soluble MR-Imaging Probes.

The particles of the invention may bear hydrophobic substituents bound to the surface of the chelating cage so as to make them insoluble.

15 Said hydrophobic substituents comprise for example aliphatic chains conjugated to the paramagnetic complex through an ester or amide bond.

The particles may alternatively consist of an insoluble macromolecular component (e.g. chitosan or derivatives) to which the paramagnetic complexes are covalently bound or into which the paramagnetic complex is entrapped
20 inside the macromolecular network through non-covalent interactions.

Preferably, the paramagnetic complex is a Gd(III) chelate, a Mn(II) or a Mn(III) chelate.

Non-covalent interactions with the macromolecular component may be obtained by using paramagnetic complexes endowed with a residual negative
25 charge, for instance Gd(III), Mn(II) or Mn(III) chelates endowed with a residual negative charge.

Alternatively, the Gd complexes particle - similarly to the procedures used for particles based on iron oxides - can be partially or completely

covered with a polymeric substrate such as dextran or other materials. This treatment on the particulate surface has also the function of controlling the residence time of the system in the blood circuit. The material covering the particulate can be functionalised with one or more synthons able to recognise
5 at molecular level specific units present on the surface of the target cell. After recognition, internalisation occurs analogously to what observed with suitably functionalised iron oxides (for example in the case of binding to transferrin receptor).

When a particle containing paramagnetic chelates ("relaxometrically
10 silent") is degraded by a suitable enzyme, single units of paramagnetic chelates are released. This process can be easily monitored because the release of paramagnetic chelates determines a progressive reduction of water proton longitudinal relaxation time. This fact is exemplified in Fig. 7 for one of the preferred compounds.

15 In view of these observations, other particles whose solubilisation is promoted by enzymes not naturally occurring in cells, but specifically expressed by molecular biology techniques, can be prepared. The introduction of particles in cells is a conventional technique, since it is routinely used for delivering genic material in cellular transfection processes. For cells unable of
20 phagocytotic activity one can take advantage of pinocytosis processes which are known to be activated through stimulation of cell surface receptors.

Various approaches for the preparation of particles that may subsequently undergo degradation by specific enzymes can be followed. For example, i) a given system can be rendered insoluble by cross-linking with
25 peptidic chains containing specific sequences for the enzyme of interest or ii) insoluble adducts can be formed between macromolecular systems with opposite electric charge (such as polylysine/polyglutamate) optionally functionalised in such a way that they undergo degradation by a specific

enzyme or iii) hydrophobic substituents separated from the complex surface by a spacer susceptible to enzyme action can be introduced. Complex units can be covalently bound to the macromolecules or can be entrapped into the particle's network due to specific interactions with the macromolecules
5 themselves.

In addition to enzymes, other effectors able to destroy the particulate can be considered, such as pH, ions, hormones and metabolites of the microenvironment that surrounds the particle.

The introduction of a particle into a cell appears as the most effective
10 way to entrap a large number of paramagnetic complex units. Once internalized, the particle will be progressively destroyed by enzymes or other agents and can thus form a soluble pool of contrast agent units. This approach can be of very general utility. One example deals with monitoring proliferative processes starting from mother cells wherein the particulate has
15 been internalised. Cellular division processes and delineation of regions wherein resulting cell progenies localise are particularly important in applications concerning stem cells.

Other examples of applications might concern the localisation of cells with macrophagic activity which are highly relevant in the formation of
20 atherosclerotic plaques and in other pathologies.

As an example, a particle based on Gd(III) complexes is represented by a GdDTPA derivative wherein two carboxy groups have been derivatized with hydrophobic chains that make the system insoluble.

The long aliphatic chains are bound to the Gd(III) chelate surface by an
25 ester function, which is hydrolysed by esterase, thus releasing soluble derivatives of the Gd(III) complex and progressively disrupting the particulate as schematized in the enclosed Figure 7. Since the amount of soluble complex (which significantly contributes to increase the relaxation rate of water


protons, thus creating a contrast in the resulting MRI image by T1-weighted sequence) depends on the amount of enzyme, the method may provide a contrast agent acting as a reporter of the enzymatic activity in the concerned cell.

- 5 As an additional example, an analogous system containing peptidic bonds in place of the ester functionality has been prepared and their cleavage by a proper proteinase enzyme assessed.

Example 1

10 Synthesis of aliphatic chains-disubstituted DTPA and complex thereof with Gd(III)

The ligand was synthesised by reaction of DTPA-bisanhydride with $\text{H}_2\text{N}-\text{CH}_2-\text{CH}_2-\text{O}-\text{CH}_2-\text{CH}_2-\text{OOC}-\text{C}_{17}\text{H}_{35}$. The ligand (slightly soluble in water) was complexed with GdCl_3 to give the insoluble chelate that precipitates as white powder (complex Gd-1).



15 Example 2

"In Vitro" evaluation of esterase activity on Complex Gd-1

- The activity of two different enzymes (esterase from swine liver [EC3.1.1.1] and lipase from *Chromobacterium viscosum* [EC 3.1.1.34]) was evaluated on Gd-1 particles. In the presence of the enzyme, in HEPES buffer
- 20 50 mM at pH = 8 and 310K, the suspension of Gd-1 shows a progressive decrease in turbidity, which suggests the formation of a soluble Gd(III) complex.

This behaviour was confirmed by measurements of the water protons

relaxation rate (R_1) on a NMR spectrometer (Stelar Spinmaster) operating at 0.5T and 298K.

As shown in Figure 1, in the absence of enzyme, R_1 does not change and its value is not different from that of pure water (0.38 s^{-1}), which reflects
5 the limited contribute of the Gd-complex on the particles surface and/or of the small amount of the complex that might be dissolved.

In the presence of the esterase (2 mg) R_1 rapidly rises and after 2-3 hours reaches the value expected for a soluble Gd(III) complex resulting from the hydrolysis of the ester bonds of the Gd-1 complex. The differences in the
10 two observed curves, and therefore the different reaction kinetics, can be ascribed to the different amounts of active units per mg of the two enzymes added to the Gd complex suspension.

Afterwards, the macrophages esterase was tested. For this purpose, about 4×10^6 macrophages were subjected to lysis by sonication and about 1
15 mg Gd-1 was added to the lysate. The enzyme present in the cellular lysate rapidly cleaves the hydrophobic ester groups, thus releasing the soluble Gd complex. The formation of soluble Gd complex is well followed by the increase of water proton relaxation rate (Fig. 2). After about two hours the enzymatic reaction reaches the steady state.

20 **Example 3**

Phagocytic uptake of Gd-1 on U937 monocytes.

The phagocytic uptake of the Gd-1 particles was carried out on U937 monocytes previously treated for three days with TPA to induce cell differentiation. The size of the Gd-1 particles was determined by electron
25 microscope observation and the measured diameter ranged from 0.5 to 10 μm . Most particles had diameter $< 10 \mu\text{m}$, which is sufficiently small to allow the phagocytic process. The uptake was carried out at 37°C and the cells were incubated with two different amounts of Gd-1 at subsequent times (1 to 12

hours). After incubation at 37°C for several hours, the medium was removed and the cells were washed three times with 5 mL PBS. In these conditions, Gd-1 particles suspended in the medium are not solubilised; in fact, the relaxivity of the medium remains very close to that of pure water (0.45 s^{-1}).

- 5 The amount of Gd(III) detected in the cells is directly proportional to incubation time and in 12 hours the saturation of the kinetic curve is not reached (Fig. 3). As expected, the amount of phagocytosed Gd(III) is proportional to the amount of complex added to the culture medium at time zero. It is interesting to compare this behaviour with the water proton
10 relaxation rate in the cytosolic extract. This was obtained by freezing three times the cells at -80°C after completion of phagocytosis. The relaxation rate in the cytosolic extract is proportional to the incubation time, but it tends to a plateau (Fig. 4), contrary to what observed in the case of the total amount of phagocytosed Gd(III). The large amount of internalised complex probably
15 inhibits the action of the enzymes involved in the hydrolysis.

A control experiment consisting in the uptake of a Gd soluble complex by macrophages was then carried out in order to ascertain whether the Gd internalised into the cells derives from any Gd-1 dissolved in the medium.

- For this purpose different amounts of Gd-HPDO3A (commercially
20 available) were incubated with cells in the same conditions as those used in the presence of Gd-1 particles. The relaxation rate of water protons measured in the cytosolic extract indicates the complete absence of Gd-HPDO3A in the cells. In this way it was demonstrated that the macrophages surface lacks specific or aspecific receptors able to internalise a complex such as Gd-
25 HPDO3A.

Example 4

"In vivo" evaluation of intracellular esterase activity on Gd-1

An experiment for evaluating the enzymatic activity inside intact cells

was set up, using Gd-1 particles as probes. For this purpose, different capsules containing about 2×10^6 cells (U937 monocytes differentiated to macrophages as described above) were incubated with ca. 5 mg of Gd-1 particles suspended in 5 mL medium (RPMI) for four hours at 37°C. After this period the cells
5 were washed three times with PBS, covered with further 5 ml RPMI and re-incubated for different times at 37°C. In this way it was possible to isolate the contribution deriving from the esterase-catalysed hydrolysis of Gd-1 particles for the time interval that depends on the internalisation step. The proton relaxation rate was measured at successive time intervals (0.5, 1, 2 hours).
10 After 4 hours incubation in the presence of Gd-1 particles the cells internalise about 60 nmol complex, but only 50% of the internalised particles is hydrolysed in this time and contributes to the total relaxivity. In fact, the relaxivity of the cytosolic extract is 2.5 when the cells are resuspended in a medium devoid of Gd-1 and raises to 3.7 in the following two hours of
15 enzymatic hydrolysis. It can be therefore assumed that 80% of Gd-1 internalised particles have been solubilised by cellular esterases (Fig. 5).

Example 5

Preparation of small particles by an ultrasound treatment

In order to prepare smaller particles of Gd-1, the gross particles
20 suspension has been undergone to ultrasound treatment. The sonochemical apparatus is a TEKIMP model (Castelfranco Veneto Tv, Italy). An aqueous suspension of Gd-1 (50 mg/ 7 ml) has been prepared in the teflon tube of apparatus. The conditions of sonication were the following: frequency: 18.2 KHz, power: 250W, time: 10min. The suspension is maintained at a
25 temperature < 5°C by a cooling system. Then the sonicated suspension has been filtered (cut off 0.8 μ M). The content of Gd in the filtrate corresponds to 10-20% of the total Gd contained in the starting suspension.

Example 6**Labelling of Neutrophiles with Gd-1**


One of the applications for labelled cells deals with the identification of infection loci in patients affected by fever of unknown origin. This imply the
5 labelling of Neutrophiles obtained from the standard procedures from a specimen of blood drawn from the patient. After labelling the neutrophiles have to be re-injected in the patient who is subjected to MRI examination.

The labelling of neutrophiles (ca. 2.5×10^6) has been carried out by incubating them (5 ml) in a medium containing 0.4 mg of particles of Gd-1
10 prepared according to example 5.

After 2.5 h of incubation at 37°C, the cells were harvested, whashed several times with PBS, then analyzed. The content of Gd per mg protein is 8.8×10^{-8} moles, i.e. an amount that after the intracellular degradation of the particle, is well sufficient to allow the visualization of the labelled cells by
15 MRI techniques.

Example 7**Labelling of Macrophages with Gd-1 after ultrasound treatment**

The particles obtained by the sonication procedure described in example 5 has been tested in an internalization assay with the U937 cells endowed with
20 macrophagic activity. The incubation medium contains 0.2 mg of Gd-1 (total). After ca. 4 hours of incubation the amount of Gd internalized reached a maximum value of 2×10^{-8} moles/ mg of protein. This means that ca 10% is taken up by the cells. Such amount is well sufficient to allow the visualisation of these cells. Once the enzymatic degradation process proceeds the signal
25 intensity progressively increases to reach a steady state which lasts for a time long enough for the type of applications of this protocol.

Example 8Synthesis of Gd-2

Gd-2

5 The product was prepared by solid phase synthesis, using Rink Amide resin.

The amino group of 11-aminoundecanoic acid was previously Fmoc protected then bound to the resin with the classical Fmoc-a.a. protocol for Solid Phase Peptide Synthesis.

10 To the swelled resin¹ in DMA, 6 consecutive couplings (N-Fmoc-11-aminoundecanoic acid, N-Fmocleucine \times 4, and maleylamido-LISINO-derivative) were carried out in the presence of PyBop, HOBt and DIPEA.

The Fmoc- deprotection was done with piperidine and the final cleavage of the resin with Reagent B. The raw material was washed with DMA, CH₂Cl₂ and diethyl ether and purified by HPLC.

The maleoyl derivative of the LIS-DTPA was obtained by simple reaction with maleic anhydride in CH₂Cl₂ of the Known LIS-DTPA ligand. The Gd-complex has been obtained by the usual procedure with GdCl₃. The G-complex is a pale yellow solid insoluble in water.

20 **Example 9**

"In vitro" evaluation of proteinase activity on Gd-2 particles

To a suspension of Gd-2 in water (30 mg/ml) a small aliquot (ca 1 mg) of the proteolytic enzyme MMP-12 has been added. Such enzyme is expected to cleave peptidic bonds. The suspension is stirred at ambient temperature for

1h. Then an aliquot (0.1 ml) of the supernatant has undergone to T1-measurement on a Stellar Spinmaster spectrometer operating at 20 MHz. R1 of 0.85 s^{-1} has been measured. An analogous experiment was carried out upon a prolonged reaction time (4 h) and R1 was found to be 1.8 s^{-1} . This observation can be explained in terms of the cleavage of the insolubilizing synthon with the release of a soluble Gd-chelate.

Example 10

Biodegradable Particles made by an insoluble macromolecular system entrapping soluble Gd chelates.

10 The nanoparticle can be formed by an insoluble matrix which entraps soluble Gd chelates. The matrix is biodegradable by the action of specific enzymes. As the intracellular degradation proceeds, a release of soluble Gd-chelate takes place which, in turn, results in an increase of signal in the resulting MR images.

15 An example of this class of biodegradable particles for MRI applications is obtained by forming nanoparticles of chitosan and Gd-DTPA. By following well established procedures for the formation of nanoparticles (mean diameter around 250 nm) it has been possible to entrap ca. 6-9 mg of Gd per 100 mg of chitosan.

20 5 mg of nanoparticles of chitosan entrapping Gd-DTPA has been added to a Petri disk containing 4×10^6 U937 cells. After 6 h of incubation at 37°C , the cells are harvested and washed several times with PBS. Then the amount of internalized Gd has been determined by ICP. It has been found that the amount of internalized Gd (9.8×10^{-8} moles / mg of protein) is well sufficient
25 for the MRI visualisation.